



CONSTRUCTION SPECIFICATION FOR  
COLD MIXED, COLD LAID, OPEN AND DENSE  
GRADED BITUMINOUS MIX

---

TABLE OF CONTENTS

309.01	SCOPE
309.02	REFERENCES
309.03	DEFINITIONS
309.04	SUBMISSION AND DESIGN REQUIREMENTS
309.05	MATERIALS
309.06	EQUIPMENT
309.07	CONSTRUCTION
309.08	QUALITY ASSURANCE
309.09	MEASUREMENT FOR PAYMENT
309.10	BASIS OF PAYMENT

APPENDICES

309-A	Commentary
-------	------------

309.01 SCOPE

This specification covers the requirements for production and placement of cold mixed, cold laid, open and dense graded bituminous mix and cover aggregate.

309.01.01 Significance and Use of Appendices

Appendices are not a mandatory part of the specification unless invoked by the Owner.

**Appendix 309-A** is a commentary appendix to provide designers with information on the use of the specification in a Contract.

## 309.02

## REFERENCES

This specification refers to the following standards, specifications, or publications:

### Ontario Provincial Standard Specifications, Construction

OPSS 302	Priming Granular Base
OPSS 304	Single and Double Surface Treatment
OPSS 310	Hot Mix Asphalt

### Ontario Provincial Standard Specifications, Material

OPSS 1003	Aggregates - Hot Mix Asphalt
OPSS 1103	Emulsified Asphalt

### Ministry of Transportation Publications

MTO Laboratory Testing Manual:

LS-263	Resistance to Plastic Flow of Bituminous Mixtures Using Marshall Apparatus
LS-265	Percent Air Voids in Compacted Dense Bituminous Pavement Mixtures
LS-266	V.M.A. in Compacted Bituminous Mixtures
LS-281	Percent Compaction of Compacted Bituminous Pavement Mixtures
LS-282	Quantitative Extraction of Asphalt Cement and Analysis of Extracted Aggregate from Bituminous Paving Mixtures
LS-301	Mix Design for Cold Mixed Dense Graded Bituminous Mixtures
LS-302	Coating Dense Graded Aggregates
LS-303	Percent Moisture Pickup in Compacted Dense Graded Bituminous Mixtures
LS-304	Coating Open Graded Aggregates
LS-305	Run Off for Open Graded Mixtures
LS-602	Sieve Analysis of Aggregates

## 309.03

## DEFINITIONS

For the purpose of this specification, the following definitions apply:

**CL mix** means cold mixed, cold laid, open or dense graded bituminous mix.

**Fat Spot** means an area of pavement substantially blacker than the surrounding pavement.

**Segregation** means a condition of the pavement characterized by areas with comparatively coarser or finer texture than that of the surrounding pavement.

## 309.04

## SUBMISSION AND DESIGN REQUIREMENTS

### 309.04.01

### Mix Design

The CL mix design shall be the responsibility of the Contractor. The proposed mix proportions corroborated by submission of the design proposed by the Contractor as determined by the supplier of the asphalt emulsion shall be forwarded to the Contract Administrator 5 Business Days before the start of production.

Mix proportions shall be determined using MTO test methods LS-301, LS-302, LS-304, and LS-305.

Aggregate samples shall be representative of the materials to be used and have proven compatibility, workability, and acceptable curing time with the emulsified asphalt selected.

**309.05 MATERIALS**

**309.05.01 Emulsified Asphalt**

The emulsified asphalt shall be according to OPSS 1103. The emulsified asphalt content shall be determined by laboratory testing and shall be within the limits set out in Table 1.

**309.05.02 Aggregates**

Aggregates shall meet the requirements of OPSS 1003 except that the gradations of open graded aggregates shall be according to Table 2 and dense graded aggregates shall be according to Table 3.

Sufficient aggregate to complete the work shall be stockpiled at least one week prior to use.

The gradation and physical properties of cover aggregate shall be according to Table 1 and 2 of OPSS 302.

**309.05.03 Cold Mixed, Cold Laid, Open and Dense Graded Bituminous Mix**

**309.05.03.01 General**

The CL mix shall show good asphalt dispersion, uniform coating, and cohesion.

**309.05.03.02 Open Graded Mix**

The cure time for open graded mix shall be such that the asphalt cement residue in the emulsion will not wash off the aggregate, if water is applied one hour after compaction of the mix.

**309.05.03.03 Dense Graded Mix**

Dense graded mix shall be according to Table 4.

**309.06 EQUIPMENT**

**309.06.01 Production and Placement**

Mobile or stationary mixing plants shall be capable of producing a uniform thoroughly blended CL mix consisting of aggregate and emulsified asphalt. The aggregate feed system to the mixing unit shall be equipped with a means of determining the mass of material being deposited into the mixing unit prior to the addition of the emulsified asphalt. The mixing unit shall be capable of continuously maintaining the amount of emulsified asphalt added within  $\pm 0.2\%$  of the aggregate by weight. All measuring devices shall be calibrated according to the manufacturer's specifications at the start of the Contract and whenever deemed necessary by the Contract Administrator. The emulsified asphalt supply system shall be equipped with a flow meter and a total delivery meter.

A Midland Mix Paver or a central mixing plant, according to the Cold Mix Plants subsection, will be considered acceptable equivalents for the production of CL mixes.

Production equipment shall be properly equipped and adjusted to provide a CL mix according to this specification.

Mechanical pavers may be used to place CL mixes produced in a central mix plant and shall be according to the Paving Equipment clause of OPSS 310.

**309.06.02 Cold Mix Plants**

**309.06.02.01 General Requirements**

The equipment shall be such that the CL mix produced meets this specification and shall demonstrate adequate control and documentation of the CL mix materials for monitoring and production purposes.

**309.06.02.02 Emulsified Asphalt Storage**

A suitable holding tank, which has been thoroughly cleaned of any other material, shall be used.

**309.06.02.03 Aggregate Feed System**

A separate tapered cold feed bin with a minimum capacity of 6.0 m<sup>3</sup> shall be provided for each size, type, or gradation of aggregate. Partitions of sufficient height to eliminate intermingling of the aggregate shall be provided between adjoining bins. Bins shall be a minimum of 0.5 m wider than the width of the loading buckets.

A permanent scalping screen shall cover the top of each bin to remove any oversize aggregate.

Vibratory pan feeders shall not be acceptable for proportioning aggregates.

A calibrated and manually adjustable feed gate shall regulate the flow of aggregate from each bin to a conveyor feeding the pugmill. The conveyor shall be equipped with a scale indicating tonnes per minute of production and total tonnes.

**309.06.02.04 Pugmill**

The pugmill shall be an approved twin shaft type with a minimum capacity of 0.6 m<sup>3</sup> and capable of producing a uniform mix. The clearance of the blades from the inner surfaces of the pugmill shall not exceed 20 mm. The paddles shall be of a type adjustable for angular position and reversible to retard the flow of the mix if required.

The mixing time or cycle shall be adjustable.

**309.06.02.05 Emulsified Asphalt Pump**

The pump shall be a variable speed positive displacement pump that feeds an adjustable spray bar located at the charging end of the pugmill. The pump may also be a positive displacement pump mechanically interlocked to the aggregate feed rate mechanism, in which case, the pump must be equipped with a variable speed control.

The pump shall be equipped with a totalizing type meter with manual reset and shall indicate the flow of emulsion being pumped in litres per minute.

There shall be a satisfactory means of positive control between the flow of aggregate from the hopper and emulsion from the pump. The pump shall be interlocked, either mechanically, electrically, or hydraulically, to the aggregate feed rate control mechanism so that a constant volumetric ratio of emulsion to aggregate is fed to the pugmill.

The system shall be interlocked through a master control switch.

**309.06.02.06 Discharge Holding Hopper**

The plant shall be equipped with a discharge holding hopper with a minimum capacity of 1.0 tonne. It shall be operated by a control switch on the control station panel.

**309.06.03                      Rollers**

Rollers shall be according to OPSS 310, except that three wheel rollers will not be allowed.

**309.06.04                      Cover Aggregate Spreaders**

Spreaders shall be according to OPSS 304 or shall be an acceptable tailgate type spreader capable of uniform application without displacement of the CL mix.

Spinner type spreaders are not allowed.

**309.07                              CONSTRUCTION**

**309.07.01                      Emulsified Asphalt**

Emulsified asphalt shall be thoroughly mixed with the aggregate.

**309.07.02                      Cold Mixed, Cold Laid, Open and Dense Graded Bituminous Mixes**

**309.07.02.01                  Operational Constraints**

Traffic shall not be permitted on the CL mix until final rolling is completed and the mix can support traffic loading without deformation.

CL mixes shall not be produced prior to May 15<sup>th</sup> or when rain is imminent. Except by special permission from the Contract Administrator, dense graded mix shall not be produced after September 15<sup>th</sup>, and open graded mix shall not be produced after September 30<sup>th</sup>. In no case shall CL mixes be produced unless the ambient temperature is at least 10 °C and rising.

**309.07.02.02                  Preparation of the Foundation**

**309.07.02.02.01              Granular Base**

The granular base on which the CL mix is to be placed shall be smooth, true to grade, and free of surface float.

**309.07.02.02.02              Pavement**

Paved surfaces on which the CL mix is to be placed shall be free of dirt, sand, foreign matter, and loose material.

**309.07.02.03                  Production and Placement**

CL mix of the type specified in the Contract Documents shall be produced and placed in accordance with the requirements of this specification.

When a second course is specified in the Contract Documents, any loose cover aggregate shall be swept from the surface. The previously laid course shall be adequately cured prior to placing the second or surface course.

**309.07.02.04                  Compaction**

**309.07.02.04.01              General**

Initial rolling shall commence once initial breaking of the asphalt emulsion has occurred and the mix can support the roller without shoving.

Final rolling shall be done using a steel tandem roller after the cover aggregate has been applied.

**309.07.02.04.02            Open Graded Mix**

Each completed course of open graded mix shall have the following percent air voids in the compacted CL mix as determined by LS-265:

- CL2 and CL3 - 15-20% Air Voids
- CL4 and CL8 - 20-30% Air Voids

**309.07.02.04.03            Dense Graded Mix**

Each completed course of dense graded mix shall be compacted to at least 94% of laboratory density as determined LS-281.

**309.07.02.05                Trial Application**

At the start of the Contract, a trial area, 200 m in length and one traffic lane wide, shall be constructed to demonstrate that equipment, personnel, and methods of operation to be used are capable of producing an acceptable CL mix.

If deficiencies are evident during construction of the trial area, work shall be stopped until the deficiencies are corrected.

**309.07.02.06                Surface Tolerance**

Each course, after final compaction, shall be smooth and true to the established crown and grade and the surface of each course shall be free from deviations exceeding 6 mm as measured in any direction with a 3 m straight edge.

**309.07.02.07                Surface Appearance**

Each course, after final compaction, shall be of uniform texture and shall be free of segregation, fat spots, oil spills, or any other defect. Defective areas shall be removed and replaced with acceptable mix of the same type and compacted to the satisfaction of the Contract Administrator.

**309.07.02.08                Sampling**

Samples of the actual CL mix shall be taken by the Contractor at least twice a day and provided to the Contract Administrator. Each sample shall fill a four-litre pail.

Additional samples shall be provided when requested by the Contract Administrator.

**309.07.02.09                Tolerances**

The mix samples shall be according to the following tolerances:

Residual asphalt content:            ± 0.3%

Aggregate retained on the 4.75 mm sieve:

For open graded mix                ± 2.0%

For dense graded mix               ± 6.0%

**309.07.03                    Cover Aggregate**

After the initial rolling has taken place, cover aggregate shall be spread uniformly at a rate of  $5 \pm 1.5 \text{ kg/m}^2$  over the surface of all open graded mixes and then rolled into the CL mix.

**309.07.04                    Management of Excess Material**

Management of excess material shall be as specified in the Contract Documents.

**309.08                        QUALITY ASSURANCE**

**309.08.01                  Testing**

The Owner may test any samples required by this specification for conformance to specified requirements.

**309.09                        MEASUREMENT FOR PAYMENT**

**309.01.01                  Actual Measurement**

**309.09.01.01              Emulsified Asphalt**

Measurement shall be by mass in kilograms according to the requirements of the Contract Documents, except that portable and conveyor scales will not be acceptable for use.

- 309.09.01.02              Open Graded CL 2**
- Open Graded CL 3**
- Open Graded CL 4**
- Open Graded CL 8**
- Dense Graded CL**
- Cover Aggregate**

Measurement shall be by mass in tonnes according to the requirements of the Contract Documents.

**309.10                        BASIS OF PAYMENT**

- 309.10.01                  Emulsified Asphalt - Item**
- Open Graded CL 2 - Item**
- Open Graded CL 3 - Item**
- Open Graded CL 4 - Item**
- Open Graded CL 8 - Item**
- Dense Graded CL - Item**
- Cover Aggregate - Item**

Payment at the Contract price for the above items shall be full compensation for all labour, Equipment, and Material to do the work.

Defective areas shall be removed, replaced with acceptable mix of the same type, and compacted to the satisfaction of the Contract Administrator at no extra cost to the Owner.

**TABLE 1**  
**Emulsified Asphalt and Residual Asphalt Content**

<b>Type of Mix</b>	<b>Emulsified Asphalt Content kg/t</b>	<b>Residual Asphalt Content by Mass (Note 1)</b>
CL 2 Open Graded, Surface or Levelling Course	69-122	4.5 - 8.0%
CL3 Open Graded, Surface or Levelling Course	65-115	4.2 - 7.5%
CL4 Open Graded, Binder or Levelling Course	61-107	4.0 - 7.0%
CL8 Open Graded, Binder or Levelling Course	55-77	3.5 - 5.0%
Dense Graded	61-107	4.0 - 7.0%
Note: 1. As determined by test LS-282.		

**TABLE 2**  
**Gradation Requirements for Open Graded Aggregates, LS-602**

<b>Sieve Designation</b>	<b>% Passing</b>			
	<b>CL 2</b>	<b>CL 3</b>	<b>CL 4</b>	<b>CL 8</b>
26.5 mm				100
19.0 mm			100	95-100
16.0 mm		100	96-100	65-90
13.2 mm	100	96-100	67-86	--
9.5 mm	75-100	50-73	29-52	20-55
6.7 mm	0-40	--	--	--
4.75 mm	0-10	0-10	0-10	0-10
2.36 mm	0-5	0-5	0-5	0-5
75 µm (Note 1)	0-2	0-2	0-2	0-2
Note: 1. Open graded mix aggregates with more than 2.0 percent passing the 75 µm sieve will be rejected.				



**TABLE 3**  
**Gradation Requirements for Dense Graded Aggregates, LS-602**

Sieve Designation	% Passing
16.0 mm	100
13.2 mm	75-95
9.5 mm	50-80
4.75 mm	25-50
1.18 mm	10-40
300 μm	2-20
150 μm	0-10
75 μm (Note 1)	0-5

Note:  
1. Dense graded mix aggregates can have a maximum variability of 2.0 percent for material passing the 75 μm sieve.

**TABLE 4**  
**Physical Requirements for Cold Mixed Dense Graded Bituminous Mix**

Property of Laboratory Compacted Mixtures	Air Cured	Water Cured	MTO Test Method
Marshall Stability, N	4500 Min.	3300 Min.	LS-263
Marshall Flow Units of 0.25 mm	10 Min.	8 Min.	LS-263
% Air Voids	4-12	--	LS-265
% VMA Pass 4.75 mm by Mass			LS-266
25%	12.0	--	
37.5%	13.25	--	
50%	14.5	--	
% by Mass Moisture Pick-up	--	2 Max.	LS-303

## **Appendix 309-A, Commentary for OPSS 309, November 2006**

**Note:** This appendix does not form part of the standard specification. It is intended to provide information to the designer on the use of this specification in a contract.

### **Designer Action/Considerations**

The designer should specify the following in the Contract Documents:

- Type of CL mix. (309.07.02.03)

The designer should determine if the following is required and, if so, specify it in the Contract Documents:

- Second course of CL mix. (309.07.02.03)

The designer should ensure that the Ontario Provincial Standards General Conditions of Contract and the 100 Series General Specifications are included in the Contract Documents.

### **Related Ontario Provincial Standard Drawings**

None.